



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification :</b>  <b>C08K 3/34, C08L 23/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 92/13029</b>  <b>(43) International Publication Date:</b> 6 August 1992 (06.08.92)
<b>(21) International Application Number:</b> PCT/SE92/00029 <b>(22) International Filing Date:</b> 20 January 1992 (20.01.92)  <b>(30) Priority data:</b> 9100181-8                      22 January 1991 (22.01.91)      SE  <b>(71) Applicant (for all designated States except US):</b> NESTE OY [FI/FI]; Keilaniemi, SF-02150 Espoo (FI).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only) :</b> GUSTAFSSON, Bill [SE/SE]; Dragonvägen 8, S-444 41 Stenungsund (SE). OLSSON, Sune [SE/SE]; Stengodsvägen 3, S-444 95 Ödsmål (SE). FRIMAN, Bo [SE/SE]; Värmlöksvägen 13, S-444 45 Stenungsund (SE).		<b>(74) Agent:</b> AWAPATENT AB; Box 5117, S-200 71 Malmö (SE).  <b>(81) Designated States:</b> AT, AT (European patent), AU, BB, BE (European patent), BF (OAPI patent), BG, BJ (OAPI patent), BR, CA, CF (OAPI patent), CG (OAPI patent), CH, CH (European patent), CI (OAPI patent), CM (OAPI patent), CS, DE, DE (European patent), DK, DK (European patent), ES, ES (European patent), FI, FR (European patent), GA (OAPI patent), GB, GB (European patent), GN (OAPI patent), GR (European patent), HU, IT (European patent), JP, KP, KR, LK, LU, LU (European patent), MC (European patent), MG, ML (OAPI patent), MN, MR (OAPI patent), MW, NL, NL (European patent), NO, PL, RO, RU, SD, SE, SE (European patent), SN (OAPI patent), TD (OAPI patent), TG (OAPI patent), US.  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> PROCESS FOR ELIMINATING ODOUR/TASTE-PRODUCING SUBSTANCES IN PLASTIC MATERIALS  <b>(57) Abstract</b>  <p>A process for eliminating in plastic materials odour/taste-producing substances is described, the plastic material especially having the shape of water pipes, plastic containers or plastic film/sheeting for packing foodstuffs and pharmaceutical preparations, or interior fittings of plastic. In the process, there is added, during processing in the molten state, less than 0.5 wt.-%, preferably 0.05-0.3 wt.-%, of a substantially hydrophobic aluminium silicate molecular sieve having a pore diameter of at least 5.5 Å, and a Si/Al molar ratio in the crystal lattice of at least 35, preferably 200-500, and a sorption capacity for water at 25 °C and 4.6 torr of less than 10 wt.-%, to the plastic material which subsequently is formed. The molecular sieve preferably has an average particle size not exceeding about 5 µm. The plastic material is a polyolefin plastic and is preferably selected among ethylene plastics and propylene plastics.</p>		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FI	Finland	MI	Mali
AU	Australia	FR	France	MN	Mongolia
BB	Barbados	GA	Gabon	MR	Mauritania
BE	Belgium	GB	United Kingdom	MW	Malawi
BF	Burkina Faso	GN	Guinea	NL	Netherlands
BG	Bulgaria	GR	Greece	NO	Norway
BJ	Benin	HU	Hungary	PL	Poland
BR	Brazil	IE	Ireland	RO	Romania
CA	Canada	IT	Italy	RU	Russian Federation
CF	Central African Republic	JP	Japan	SD	Sudan
CG	Congo	KP	Democratic People's Republic of Korea	SE	Sweden
CH	Switzerland	KR	Republic of Korea	SN	Senegal
CI	Côte d'Ivoire	LI	Liechtenstein	SU	Soviet Union
CM	Cameroon	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
DE	Germany	MC	Monaco	US	United States of America
DK	Denmark	MG	Madagascar		
ES	Spain				

PROCESS FOR ELIMINATING ODOUR/TASTE-PRODUCING  
SUBSTANCES IN PLASTIC MATERIALS

The present invention relates to a process for eliminating odour/taste-producing substances in plastic materials. The invention particularly relates to the elimination of undesired, unintentionally added, odour/taste-producing substances from polyolefin type materials, by which are henceforth meant homopolymers of ethylene or propylene or copolymers of one of these hydrocarbons with another alpha olefin, intended for fields of application where they may contact liquids or foodstuffs to be consumed by human beings or animals, or where any odour or taste may be experienced as negative for hygienic or aesthetic reasons.

In many contexts undesired, odour- and/or taste-producing substances appear owing to chemical degradation or transformation in connection with production or compounding of plastic materials. These substances can be of a highly varying chemical character. The occurrence thereof can constitute a health hazard or merely a source of irritation. Since the human being normally is most susceptible to odours and tastes, the substances need not appear in very high concentrations, but in most cases as low concentrations as one or a few ppm are sufficient to make a taste or odour evident. To date, attempts have been made to overcome or at least reduce such odour and taste problems in various ways, such as by degassing the plastic material. Such a method is not only lengthy and expensive; it also results in but a moderate improvement in respect of odour and taste, respectively.

Some specific fields will now be mentioned where the problem with undesired substances causing odour and/or taste is of particular significance.

Such a field comprises plastic pipes, more specifically plastic water pipes, where the emission of odour- and/or taste-producing substances from the plastic mate-

rial to the drinking water flowing through the pipe frequently is an annoying problem which is difficult to solve. The problem grows more serious by the fact that no details of the odour/taste-producing substance(s) are known. It is believed that they consist of a variably composed mixture of different substances, such as oligomers, formed in the polymerisation, or volatile substances which have been formed by oxidisation processes in conjunction with subsequent steps of processing and which even at further small concentrations of about 1-1000 ppm in the water give this an undesired odour and/or taste.

A second field comprises film and sheeting of plastic material, more particularly film and sheeting that is caused to contact foodstuffs and pharmaceutical preparations. Since for foodstuffs and pharmaceutical preparations extremely high requirements as regards purity are made and no foreign substances contaminating the foodstuff or pharmaceutical preparation are allowed for reasons of health and security, it is vital that plastic film and sheeting used for such products does not emit any undesired or contaminating substances. In such plastic products, there is also a particularly great risk that undesired substances are produced, such as when boiling the foodstuff in the wrapping, or when sterilising the drug packing by heat treatment or radiation.

A closely related field is represented by containers, such as bottles, of blow-moulded or moulded plastic, for packing foodstuffs, beverages or pharmaceutical preparations.

A further field applies to interior fittings of plastic, e.g. panels, for use in buildings or cars and the like. In new cars, it thus is not unusual that the odour can be very unpleasant.

In all four fields mentioned above, the possible odour which one may want to eliminate can appear especially in the compounding/processing of the plastic

material and in this context constitutes a problem in the working environment.

From a general point of view, it is known to remove any undesired odour and/or taste by means of adsorbing substances, and as examples of such adsorbing substances, activated carbon, silica gel, activated aluminium oxide, diatomaceous earth and zeolites may be mentioned. An example in which a number of such additives are suggested, is Japanese Patent Specification JP 1,023,970 which thus is incorporated by reference. This publication suggests the adding of e.g. aluminium hydroxide, clay, diatomaceous earth, kaolin, talc, bentonite, activated carbon or activated carbon fibre for materials for packing foodstuffs to be heated in the packing. However, such additives have been found to be without any appreciable effect, except under special circumstances, in the case of undesired components in plastic materials of the types concerned according to the present invention since, as a rule, they lose their absorbing capacity when contacting water or water vapour.

Recently, US Patent Specification 4,795,482 has described a new type of zeolites intended for the elimination of undesired odour in certain contexts and supplied under one of the names ABSCENT or SMELLRITE. These zeolites are described to be crystalline, siliceous molecular sieves in which at least about 90, and preferably at least about 95, % of the tetrahedral oxide units of the crystal lattice are  $\text{SiO}_2$  tetrahedra, and which have a sorption capacity for water at 25°C and 4.6 torr of less than 10 wt.-%. These zeolites have an Si/Al molar ratio of from 35 to infinity, preferably between 200 and 500, and a pore diameter of at least 5.5 Å, preferably at least 6.2 Å. It is also preferred that the sorption capacity for water vapour at 25°C and a water vapour pressure of 4.6 torr is less than 6 wt.-%. These substantially hydrophobic molecular sieves are used to remove odorous organic compounds at a temperature of from -25°C to 100°C.

It should here be added that the above-mentioned Si/Al molar ratio for these molecular sieves applies to the oxide units of the crystal lattice only. The Si/Al molar ratio of the zeolite, which has been determined by  
5 conventional wet analysis, can be considerably lower owing to contamination by aluminous pollutants formed in the so-called dealuminification reaction which in many cases is included as a step in the production of the zeolite.

The above-mentioned zeolitic molecular sieves have  
10 proved useful above all for removing undesired odour from hygienic products, such as diapers, incontinence products and the like. Reference is here also made to EP 0,348,978.

As a further example of prior-art technique while using the same type of zeolite, US Patent 4,910,295 may be  
15 mentioned. This patent relates to a specific process for reducing the odour of residual amounts of the comonomer ethylidene norbornene present in certain types of EPDM rubber.

One more example of prior art is US 4,826,497 concerning fibrous absorbent articles, such as diapers and  
20 the like, intended for the absorption of body fluids. The diaper contains a zeolite which can be loosely arranged therein or, preferably, be immobilised.

According to the present invention, it has now surprisingly been found that by adding the above type of  
25 zeolitic molecular sieve it is possible to completely eliminate the above problem with undesired, odour- and/or taste-producing substances in plastic materials. By the term plastic material is here meant polyolefin plastic.  
30 The polyolefin plastic is preferably selected among ethylene plastic, i.e. plastic based on polyethylene or on copolymers of ethylene, in which the ethylene monomer constitutes the largest part of the mass, or propylene plastic, i.e. plastic based on polypropylene or on copolymers  
35 of propylene in which the propylene monomer constitutes the largest part of the mass.

As indicated above, the invention concerns in a special aspect a process for eliminating, in plastic materials such as plastic pipes, plastic film and sheeting, plastic containers and plastic interior fittings, low contents of odour/taste-producing substances of unknown character, which have been formed by physical and/or chemical action in the polymerisation process or the subsequent compounding/processing.

More precisely, according to the invention it has been found that the incorporation of small amounts of a substantially hydrophobic aluminium silicate molecular sieve, which preferably comprises a zeolite according to the above-mentioned US Patent 4,795,482, permits simple and more or less complete elimination of undesired odour- and/or taste-producing substances.

The characteristic features of the invention appear from the accompanying claims.

The invention is characterised in that it provides for a process for eliminating in plastic materials odour- and/or taste-producing components which have been formed in polymerisation, heat treatment or radiation.

After a number of experiments, it has been found according to the invention that not all zeolites are active. Thus, it has been established that the zeolite should be substantially hydrophobic (oleophilic) to be effective in the elimination of odour and taste. A measure of the hydrophobic properties is the water sorption of the zeolite, and this should suitably be less than 10 wt.-%, preferably less than 6 wt.-%, at 25°C and 4.6 torr. The Si/Al molar ratio of the zeolite in the oxide units of its crystal lattice seems to affect the hydrophobic properties and should exceed 35 and preferably be between 200 and 500. The pore diameter of the zeolite, which according to the molecular size determines which compounds can be caught by the zeolite, should be at least 5.5 and preferably at least 6.2 Å.

The zeolite, which generally is in the form of a powder, should have such a small particle size that it does not detrimentally affect the appearance of the plastic material or the other properties thereof. Thus, the zeolite should have an average particle size not exceeding about 10  $\mu\text{m}$ , such as about 0.1-7  $\mu\text{m}$ , preferably not exceeding about 5  $\mu\text{m}$ .

According to the invention, it has been found that a notably small amount of zeolite of less than 0.5 wt.-%, preferably 0.05-0.3 wt.-%, is sufficient to eliminate any undesired odour and/or taste. This distinguishes from earlier applications in which zeolites have normally been used in considerably higher contents.

In the process according to the invention, the aluminium silicate molecular sieve (zeolite) is added to the plastic raw material which in its molten state should be compounded to pellets or finished material. The zeolite can be added either as it is or in the form of a so-called master batch, i.e. mixed with a polymer. In the extruder or the corresponding compounding device, the components are mixed and the zeolite is uniformly distributed by dispersion in the molten polymer material. In the finished, formed plastic product, the zeolite will thus be present in this manner. It is surprising that, all the same, the zeolite can effectively produce its odour- and taste-eliminating effect, since it would have been assumed that the pores of the zeolite should be clogged by the molten plastic material. For some reason, however, this is not the case, but the zeolite can effectively catch and eliminate undesired, odour- and/or taste-causing substances.

For further elucidation of the invention an Example follows below.

#### EXAMPLE

For the purpose of determining the emission of taste-causing substances from different plastic materials, a great number of materials have been tested while using a taste panel. The testing materials have been produced by



compounding an HD polyethylene having a density of 945 kg/m<sup>3</sup> and containing normal additives that are required for stabilisation/ processing and also serving as reference material, and different molecular sieve materials at 220°C, on the one hand in a laboratory Buss-Kneter and, on the other hand, in a full-scale production line. The material was pelleted in conjunction with the extrusion. From pellets, a sample of 32 g was taken for each test, which was stirred for 4 h at a temperature of 30 ± 1°C by a magnetic agitating means in a flask fitted with a ground-in plug and containing 1000 ml of pure distilled water. Five sub-samples were then prepared from each sample by dilution according to the Table below.

TABLE

15	Sub-sample	Sample water	Dilution water	Taste/odour level
	No.	ml	ml	degree
	1	200	0	1
	2	130	70	1.5
20	3	100	100	2
	4	50	150	4
	5	25	175	8

The level of taste and odour is here defined as follows:  $(a + b)/a$  wherein a is the amount of sample water in the sub-sample in which odour or taste is barely detectable, while b is the amount of dilution water in the same sub-sample. The lower the value of the taste and odour level the better the result. A value of 1.5 and below is acceptable. Seven trained taste testers are allowed to estimate each sample and determine their personal taste level. The average value of the seven people is considered to produce an objective estimation thereof. The testing is blind, i.e. the taste panel cannot distinguish the samples.

A total of 14 samples were examined according to this procedure, and the results were as follows:

8

TABLE 2

	Sample	Addi- tive	Con- tent wt.-%	Pro- cess- ing	Panel Estimate Sub-sample No.					Taste Level
					1	2	3	4	5	
5	1			P	7	7	6	6	5	>8
	2			P	6	6	6	6	5	>8
	3	A3	0.22	P	7	7	7	7	6	>8
	4	A3	0.22	P	6	6	6	5	3	4-8
10	5	A3	0.22	P	7	7	7	6	1	4-8
	6	A10	0.12	P	7	7	6	6	4	>8
	7	A10	0.11	P	7	7	7	7	6	>8
	8	A10	0.10	P	7	7	7	6	4	>8
	9	ABSC	0.27	P	2	1	1	0	0	<1
15	10	ABSC	0.27	P	5	3	2	1	0	1-1.5
	11	ABSC	0.28	P	3	2	1	0	0	<1
	12	ABSC	0.25	B	0	0	0	0	0	<1
	13	ABSC	0.10	B	0	0	0	0	0	<1
	14	ABSC	0.05	B	0	0	0	0	0	<1

20

A3 and A10 are common, non-hydrophobic zeolites which are supplied by Grace GmbH under the tradename "Sylosiv 3A" and "Sylosiv 10A", respectively. ABSC stands for ABSCENT which is the tradename of a zeolite produced according to US Patent 4,795,482. "P" implies that the sample has been run on a production scale in a compounding line, whereas "B" implies that the sample has been run on a laboratory scale in a small Buss-Cokneter. The figures under the heading "Panel Estimate" state how many of the people in the taste panel which have noticed the taste in the sub-sample 1, 2, 3, 4 and 5 of the respective main sample. Table 2 shows that the adding of conventional zeolite (Samples 3-8) produces no effect or a very poor effect in respect of eliminating odour/taste-causing substances, whereas the adding of a zeolite according to the invention (Samples 9-14) gives an excellent result.

## CLAIMS

1. Process for eliminating in plastic materials  
5 odour/taste-producing substances, c h a r a c t e r -  
i s e d in that the plastic material is selected among  
ethylene plastics or propylene plastics, and that to said  
plastic material, during processing in the molten state,  
there is added less than 0.5 wt.-% of a substantially  
10 hydrophobic aluminium silicate molecular sieve having a  
pore diameter of at least 5.5 Å, an Si/Al molar ratio in  
the crystal lattice of at least 35, and a sorption capa-  
city for water at 25°C and 4.6 torr of less than 10 wt.-%.
2. Process as claimed in claim 1, c h a r a c -  
15 t e r i s e d in that the molecular sieve added has an  
Si/Al molar ratio in the crystal lattice of between 200  
and 500, and that it has a sorption capacity for water at  
25°C and 4.6 torr of less than 6 wt.-%.
3. Process as claimed in any one of the preceding  
20 claims, c h a r a c t e r i s e d in that the molecular  
sieve added has an average particle size not exceeding  
5 µm.
4. Process as claimed in any one of the preceding  
claims, c h a r a c t e r i s e d in that the molecular  
25 sieve is added in an amount of 0.05-0.3 wt.-%.
5. Process for eliminating, in pipes, preferably  
water pipes, of ethylene plastic or propylene plastic, the  
emission of odour/taste-producing substances, c h a r -  
a c t e r i s e d in that less than 0.5 wt.-%, preferably  
30 0.05-0.3 wt.-%, of a substantially hydrophobic aluminium  
silicate molecular sieve having an Si/Al molar ratio in  
the crystal lattice above 35, preferably 200-500, a pore  
diameter of at least 5.5 Å and a sorption capacity for  
water at 25°C and 4.6 torr of less than 10 wt.-%, is added  
35 to the plastic material, and that this is subsequently  
formed to a pipe.

6. Process for eliminating, in film or sheeting, preferably for packing foodstuffs or pharmaceutical preparations, of ethylene plastic or propylene plastic, the emission of odour- and/or taste-producing substances, characterised in that less than 0.5 wt.-%, preferably 0.05-0.3 wt.-%, of a substantially hydrophobic aluminium silicate molecular sieve having an Si/Al molar ratio in the crystal lattice above 35, preferably 200-500, a pore diameter of at least 5.5 Å and a sorption capacity for water at 25°C and 4.6 torr of less than 10 wt.-%, is added to the plastic material, and that this is subsequently formed to a film or sheeting.

7. Process for eliminating, in blow-moulded or moulded plastic bottles or containers of ethylene plastic or propylene plastic, the emission of odour/taste-producing substances, characterised in that less than 0.5 wt.-%, preferably 0.05-0.3 wt.-%, of a substantially hydrophobic aluminium silicate molecular sieve having an Si/Al molar ratio in the crystal lattice above 35, preferably 200-500, a pore diameter of at least 5.5 Å and a sorption capacity for water at 25°C and 4.6 torr of less than 10 wt.-%, is added to the plastic material, and that this is subsequently formed to a bottle or container.

8. Process for eliminating, in interior fittings, preferably for use in buildings or cars, of ethylene plastic or propylene plastic, the emission of odour-producing substances, characterised in that less than 0.5 wt.-%, preferably 0.05-0.3 wt.-%, of a substantially hydrophobic aluminium silicate molecular sieve having an Si/Al molar ratio in the crystal lattice above 35, preferably 200-500, a pore diameter of at least 5.5 Å and a sorption capacity for water at 25°C and 4.6 torr of less than 10 wt.-%, is added to the plastic material, and that this is subsequently formed to the interior fitting desired.

# INTERNATIONAL SEARCH REPORT

International Application No PCT/SE 92/00029

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (if several classification symbols apply, indicate all) <sup>6</sup> According to International Patent Classification (IPC) or to both National Classification and IPC IPC5: C 08 K 3/34, C 08 L 23/00																				
<b>II. FIELDS SEARCHED</b> <div style="text-align: center; border-top: 1px solid black; border-bottom: 1px solid black;">Minimum Documentation Searched<sup>7</sup></div> <table style="width: 100%; border-collapse: collapse;"> <tr> <th style="width: 25%; border: 1px solid black; text-align: left;">Classification System</th> <th style="width: 75%; border: 1px solid black; text-align: left;">Classification Symbols</th> </tr> <tr> <td style="border: 1px solid black; height: 40px; vertical-align: bottom;">IPC5</td> <td style="border: 1px solid black; height: 40px; vertical-align: bottom;">C 08 K; C 08 L</td> </tr> </table> <div style="text-align: center; border-top: 1px solid black; border-bottom: 1px solid black;">Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in Fields Searched<sup>8</sup></div> <p>SE,DK,FI,NO classes as above</p>			Classification System	Classification Symbols	IPC5	C 08 K; C 08 L														
Classification System	Classification Symbols																			
IPC5	C 08 K; C 08 L																			
<b>III. DOCUMENTS CONSIDERED TO BE RELEVANT<sup>9</sup></b> <table style="width: 100%; border-collapse: collapse;"> <tr> <th style="width: 10%; border: 1px solid black; text-align: left;">Category<sup>10</sup></th> <th style="width: 60%; border: 1px solid black; text-align: left;">Citation of Document,<sup>11</sup> with indication, where appropriate, of the relevant passages<sup>12</sup></th> <th style="width: 30%; border: 1px solid black; text-align: left;">Relevant to Claim No.<sup>13</sup></th> </tr> <tr> <td style="border: 1px solid black; text-align: center;">A</td> <td style="border: 1px solid black;">US, A, 4795482 (GIOFFRE ET AL) 3 January 1989, see the whole document --</td> <td style="border: 1px solid black; text-align: center;">1-8</td> </tr> <tr> <td style="border: 1px solid black; text-align: center;">A</td> <td style="border: 1px solid black;">US, A, 4826497 (MARCUS ET AL) 2 May 1989, see the whole document --</td> <td style="border: 1px solid black; text-align: center;">1-8</td> </tr> <tr> <td style="border: 1px solid black; text-align: center;">A</td> <td style="border: 1px solid black;">US, A, 4855154 (GIOFFRE ET AL) 8 August 1989, see the whole document --</td> <td style="border: 1px solid black; text-align: center;">1-8</td> </tr> <tr> <td style="border: 1px solid black; text-align: center;">A</td> <td style="border: 1px solid black;">US, A, 4910295 (BERNIER ET AL) 20 March 1990, see the whole document --</td> <td style="border: 1px solid black; text-align: center;">1-8</td> </tr> <tr> <td style="border: 1px solid black; text-align: center;">A,P</td> <td style="border: 1px solid black;">US, A, 5013335 (MARCUS) 7 May 1991, see the whole document -- -----</td> <td style="border: 1px solid black; text-align: center;">1-8</td> </tr> </table>			Category <sup>10</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>	A	US, A, 4795482 (GIOFFRE ET AL) 3 January 1989, see the whole document --	1-8	A	US, A, 4826497 (MARCUS ET AL) 2 May 1989, see the whole document --	1-8	A	US, A, 4855154 (GIOFFRE ET AL) 8 August 1989, see the whole document --	1-8	A	US, A, 4910295 (BERNIER ET AL) 20 March 1990, see the whole document --	1-8	A,P	US, A, 5013335 (MARCUS) 7 May 1991, see the whole document -- -----	1-8
Category <sup>10</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>																		
A	US, A, 4795482 (GIOFFRE ET AL) 3 January 1989, see the whole document --	1-8																		
A	US, A, 4826497 (MARCUS ET AL) 2 May 1989, see the whole document --	1-8																		
A	US, A, 4855154 (GIOFFRE ET AL) 8 August 1989, see the whole document --	1-8																		
A	US, A, 4910295 (BERNIER ET AL) 20 March 1990, see the whole document --	1-8																		
A,P	US, A, 5013335 (MARCUS) 7 May 1991, see the whole document -- -----	1-8																		
<div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> <p><b>* Special categories of cited documents:<sup>10</sup></b></p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 45%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance, the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance, the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&amp;" document member of the same patent family</p> </div> </div>																				
<b>IV. CERTIFICATION</b> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; border: 1px solid black; padding: 5px;">           Date of the Actual Completion of the International Search  <b>22nd April 1992</b> </td> <td style="width: 50%; border: 1px solid black; padding: 5px;">           Date of Mailing of this International Search Report  <b>1992 -04- 27</b> </td> </tr> <tr> <td style="border: 1px solid black; padding: 5px;">           International Searching Authority  <div style="text-align: center; margin-top: 10px;"> <b>SWEDISH PATENT OFFICE</b> </div> </td> <td style="border: 1px solid black; padding: 5px;">           Signature of Authorized Officer  <div style="text-align: center; margin-top: 10px;">   <b>Jack Hedlund</b> </div> </td> </tr> </table>			Date of the Actual Completion of the International Search <b>22nd April 1992</b>	Date of Mailing of this International Search Report <b>1992 -04- 27</b>	International Searching Authority <div style="text-align: center; margin-top: 10px;"> <b>SWEDISH PATENT OFFICE</b> </div>	Signature of Authorized Officer <div style="text-align: center; margin-top: 10px;">   <b>Jack Hedlund</b> </div>														
Date of the Actual Completion of the International Search <b>22nd April 1992</b>	Date of Mailing of this International Search Report <b>1992 -04- 27</b>																			
International Searching Authority <div style="text-align: center; margin-top: 10px;"> <b>SWEDISH PATENT OFFICE</b> </div>	Signature of Authorized Officer <div style="text-align: center; margin-top: 10px;">   <b>Jack Hedlund</b> </div>																			

**ANNEX TO THE INTERNATIONAL SEARCH REPORT  
ON INTERNATIONAL PATENT APPLICATION NO.PCT/SE 92/00029**

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.  
The members are as contained in the Swedish Patent Office EDP file on **28/02/92**  
The Swedish Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A- 4795482	89-01-03	AU-B- 602411	90-10-11
		AU-D- 1854288	89-01-05
		EP-A- 0297543	89-01-04
		JP-A- 1085113	89-03-30
		US-A- 4826497	89-05-02
		US-A- 4855154	89-08-08
		US-A- 5013335	91-05-07
US-A- 4826497	89-05-02	AU-B- 602411	90-10-11
		AU-D- 1854288	89-01-05
		EP-A- 0297543	89-01-04
		JP-A- 1085113	89-03-30
		US-A- 4795482	89-01-03
		US-A- 4855154	89-08-08
		US-A- 5013335	91-05-07
US-A- 4855154	89-08-08	JP-A- 2006659	90-01-10
		AU-B- 602411	90-10-11
		AU-D- 1854288	89-01-05
		EP-A- 0297543	89-01-04
		JP-A- 1085113	89-03-30
		US-A- 4795482	89-01-03
		US-A- 4826497	89-05-02
US-A- 4910295	90-03-20	US-A- 5013335	91-05-07
		CA-A- 2015628	90-10-28
		EP-A- 0395104	90-10-31
US-A- 5013335	91-05-07	JP-A- 2302404	90-12-14
		AU-B- 602411	90-10-11
		AU-D- 1854288	89-01-05
		EP-A- 0297543	89-01-04
		JP-A- 1085113	89-03-30
		US-A- 4795482	89-01-03
		US-A- 4826497	89-05-02
		US-A- 4855154	89-08-08